



ORG TAN SMR

APEO & VOC Free Maleic Acrylic copolymer, which can be used for retanning for all type of leather where soft and mellow feels are required

Aspect	: Pale yellow viscous liquid
Basis	: Maleic – acrylic copolymer
pH	: In 10% aqueous solution, 8.5 - 9.5
Solubility	: Good
Light fastness	: Excellent
Stability	: Stable at pH above 4.5

PROPERTIES

ORG TAN SMR

- Maintain inner softness even after wet toggling and nailing, so it is best suitable for Upholstery leather.
- Is especially suitable for filling loose fibers in upper leather.
- Imparts fullness, grain smoothness and improves the thickness.
- Excellent light fastness, so useful for white leathers and pastel shades.
- Is not compatible with mineral tanning agents.
- When used in retanning of chrome tanned leather; it improves the fullness and tightness of grain with elastic and bouncing properties.

APPLICATIONS

(All % on shaved wt.)

Upholstery	: 5-6% ORG TAN SMR
Other Articles	: 3-5% ORG TAN SMR before retanning 2-3% ORG TAN SMR after fatliquoring and before fixation

SHELF LIFE

When stored in cool & dry condition it can be stored for one year from the date of manufacturing.

Technical suggestions without any obligation.